

F-60 A/B

60 SHORE A POLYURETHANE ELASTOMER

PRODUCT DESCRIPTION:

The F-60 A/B system is a production oriented fast gel and fast de-mold material. It features a work life which allows sufficient time to vacuum de-gas and pour air-free parts. F-60 A/B can be demolded in as little as one hour depending on part size and configuration.

PRODUCT HIGHLIGHTS:

- Rapid demolds
- Ideal for part production
- Does not contain MOCA, MDA, or TDI
- Very easy to use

PHYSICAL PROPERTIES:

Hardness, Shore A ASTM D2240	60 ± 5
Density, (g/cc) ASTM D792.....	1.06
Cubic Inches per Pound.....	26
Color/Appearance.....	Translucent Pale Yellow
Tensile Strength, (psi) ASTM D412.....	685
Modulus of Elasticity, (psi) ASTM D412:	
@ 100% Strain	312
@ 200% Strain	497
@ 300% Strain	623
Elongation, (%) ASTM D412.....	300
Tear Strength, (pli) ASTM D624.....	57
Shrinkage, (in/in) linear ASTM D2566.....	0.003

Note: Reported physical properties based on elevated temperature cured test specimens.

HANDLING PROPERTIES:

Mix Ratio (by weight):	
Part A	50 parts by weight
Part B	100 parts by weight
Mix Ratio (by volume):	
Part A	46 parts by volume
Part B	100 parts by volume
Specific Gravity:	
Part A	1.13
Part B	1.03

HANDLING PROPERTIES (continued):

Viscosity, (cps) @ 77°F (25°C) Brookfield:

Part A	550
Part B	850
Mixed Viscosity	930
Work Time, (100g mass) @ 77°F (25°C)	6 - 7 minutes
Gel Time	8 - 9 minutes
Demold Time @ 77°F (25°C).....	1 - 2 hours

CURE SCHEDULE/HEAT CURING:

Most of the physical properties can be achieved in 5-7 days at ambient temperature, 77°F (25°C). In order to achieve maximum physical properties, a post cure with heat is required. BJB recommends 24 hours at ambient temperature, 77°F (25°C), followed by 16 hours at 160°F (71°C).

NOTE:

The F-60 B, in liquid form, will darken with age. Opened containers of material should be purged with dry nitrogen prior to replacing lids or caps to prevent moisture contamination. **The cure will be inhibited if cast against a tin catalyzed silicone RTV.**

STORAGE:

Store in cool dry place. Unopened containers will have a shelf life of 6 months from date of shipment when properly stored at room temperatures. Purge opened containers with dry nitrogen before re-sealing.

PACKAGING:

Gallon kits	4 lbs. A, 8 lbs. B
5-Gallon kits	20 lbs. A, 40 lbs. B
55-Gallon kits	200 lbs. A, 400 lbs. B

SAFETY PRECAUTIONS:

Use in a well-ventilated area. Avoid contact with skin using protective gloves and protective clothing. Repeated or prolonged contact on the skin may cause an allergic reaction.

Eye protection is extremely important. Always use approved safety glasses or goggles when handling this product.

IF CONTACT OCCURS:

Skin: Immediately wash with soap and water. Remove contaminated clothing and launder before reuse. It is *not* recommended to remove resin from skin with solvents. Solvents only increase contact and dry skin. Seek qualified medical attention if allergic reactions occur.

Eyes: Immediately flush with water for at least 15 minutes. Call a physician.

Ingestion: If swallowed, call a physician immediately. Remove stomach contents by gastric suction or induce vomiting only as directed by medical personnel. Never give anything by mouth to an unconscious person.

Refer to the Material Safety Data Sheet before using this product.