

Product Data

Somos[®] ProtoGen 18920

Description

DSM's Somos[®] ProtoGen 18920 is a liquid photopolymer that produces accurate, ABS-like parts ideal for general purpose applications. Somos[®] ProtoGen resins are the first stereolithography resins to demonstrate different material properties based on machine exposure control. Based on Somos[®] Oxetane[™] chemistry, Somos[®] ProtoGen 18920 offers superior chemical resistance, a wide processing latitude and excellent tolerance to a broad range of temperature and humidity, both during and after the build.

Applications

This high-temperature resistant, ABS-like photopolymer is used in solid imaging processes, such as stereolithography, to build three-dimensional parts. Somos[®] ProtoGen 18920 provides considerable processing latitude and is ideal for the medical, electronic, aerospace and automotive markets that demand accurate RTV patterns, durable concept models, highly accurate humidity & temperature resistant parts.

TECHNICAL DATA - LIQUID PROPERTIES

Appearance	Grey
Viscosity	~350 cps @ 30°C
Density	~1.16 g/cm ³ @ 25°C

TECHNICAL DATA - OPTICAL PROPERTIES

E _c	7.0 mJ/cm ²	[critical exposure]
D _p	4.20 mils	[slope of cure-depth vs. ln (E) curve]
E ₁₀	76 mJ/cm ²	[exposure that gives 0.254 mm (.010 inch) thickness]

TECHNICAL DATA							
Mechanical Properties		Somos [®] ProtoGen 18920 UV Postcure at HOC -2		Somos [®] ProtoGen 18920 UV Postcure at HOC +3		Somos [®] ProtoGen 18920 UV & Thermal Postcure	
ASTM Method	Property Description	Metric	Imperial	Metric	Imperial	Metric	Imperial
D638M	Tensile Strength	46.6 - 47.8 MPa	6.8 - 6.9 ksi	56.1 - 56.9 MPa	8.1 - 8.3 ksi	69.2 - 69.6 MPa	10.0 - 10.1 ksi
D638M	Tensile Modulus	2,103 - 2,317 MPa	305.0 - 336.0 ksi	2,577 - 2,623 MPa	373.7 - 380.4 ksi	2,544 - 2,916 MPa	369.0 - 423.0 ksi
D638M	Elongation at Break	13 - 19%	13 - 19%	5 - 12%	5 - 12%	4 - 9%	4 - 9%
D790M	Flexural Strength	73.0 - 75.0 MPa	10.6 - 10.9 ksi	85.0 - 87.0 MPa	12.3 - 12.6 ksi	92.1 - 98.1 MPa	13.4 - 14.2 ksi
D790M	Flexural Modulus	2,126 - 2,314 MPa	308.3 - 335.6 ksi	2,442 - 2,518 MPa	354.2 - 365.2 ksi	2,504 - 2,696 MPa	363.1 - 391.0 ksi
D2240	Hardness (Shore D)	85 - 86	85 - 86	86 - 87	86 - 87	86 - 88	86 - 88
D256A	Izod Impact (Notched)	0.18 - 0.28 J/m	0.26 - 0.52 ft-lb/in	0.22 - 0.26 J/m	0.41 - 0.49 ft-lb/in	0.20 - 0.24 J/m	0.37 - 0.45 ft-lb/in
D570-98	Water Absorption	0.78%	0.78%	0.74%	0.74%	0.38%	0.38%

TECHNICAL DATA					
Thermal/ Electrical Properties		Somos [®] ProtoGen 18920 UV Postcure at HOC -2		Somos [®] ProtoGen 18920 UV & Thermal Postcure	
ASTM Method	Property Description	Metric	Imperial	Metric	Imperial
E831-05	C.T.E. -40 - 0°C (-40 - 32°F)	69.4 µm/m°C	38.6 µin/in°F	64.7 µm/m°C	35.9 µin/in°F
E831-05	C.T.E. 0 - 50°C (32 - 122°F)	74.0 µm/m°C	41.1 µin/in°F	74.2 µm/m°C	41.2 µin/in°F
E831-05	C.T.E. 50 - 100°C (122 - 212°F)	106.0 µm/m°C	58.9 µin/in°F	79.2 µm/m°C	44.0 µin/in°F
E831-05	C.T.E. 100 - 150°C (212 - 302°F)	130.3 µm/m°C	72.4 µin/in°F	138.8 µm/m°C	77.1 µin/in°F
D150-98	Dielectric Constant 60 Hz	3.53	3.53	3.28	3.28
D150-98	Dielectric Constant 1 KHz	3.44	3.44	3.23	3.23
D150-98	Dielectric Constant 1 MHz	3.21	3.21	3.04	3.04
D149-97A	Dielectric Strength	15.4 - 15.9 kV/mm	391 - 403 V/mil	14.3 - 15.2 kV/mm	364 - 386 V/mil
E1545-00	Tg	6.90°C	156°F	97.5°C	208°F
D648	HDT @ 0.46 MPa (66 psi)	58.7°C	137°F	96.5°C	205°F
D648	HDT @ 1.81 MPa (264 psi)	51.0°C	123°F	78.6°C	175°F

DSM Functional Materials
Somos[®] Materials Group

in North America

1122 St. Charles Street
Elgin, Illinois 60120
USA
Phone: +1.847.697.0400

Applied Rapid Technologies

1130 International Pkwy
Fredericksburg, VA 22406
Tel: 540-286-2266
Fax: 540-286-5252
www.artcorp.com

in Europe

Slachthuisweg 30
3150 XN Hoek van Holland
The Netherlands
Phone: +31.174.315.391

Visit us online at www.dsmsomos.com

NOTICE : Somos[®] is a registered trademark of Royal DSM N.V. Somos[®] is an unincorporated subsidiary of DSM Desotech Inc. The information presented herein is based on generally accepted analytical and testing practices and is believed to be accurate. However, DSM Desotech expressly disclaims any product warranties which may be implied including warranties or merchantability and/or fitness for a particular purpose DSM Desotech's products are sold subject to DSM Desotech's standard terms and conditions of sale, copies of which are available upon request. Purchasers are responsible for determining the suitability of the product for its intended use and the appropriate manner of utilizing the product in purchaser's production processes and applications so as to insure safety, quality and effectiveness. Purchasers are further responsible for obtaining necessary patent rights to practice any invention in connection with the use of purchased product and any other product or process. DSM Desotech reserves the right to change specifications of their products without notice. © 2012 DSM IP ASSES TS B.V. All rights reserved.