

# Somos<sup>®</sup> Momentum



**Additive manufacturing, and more specifically stereolithography (SL), has enabled a faster route to market for footwear, while reducing development cost and aiding development of more complex shoe designs. With Somos<sup>®</sup> Momentum, DSM provides a compelling solution that combines rich feature detail and dimensional stability with the most efficient printing outcomes available without compromising on surface quality and dimensional accuracy.**

Footwear manufacturers face a multitude of challenges, from developing durable solutions to managing design and the range of sizes required. They continue to seek more effective means to develop new designs to meet increasingly diverse customer needs, while also striving to quicken the pace of design and innovation. Additive manufacturing for footwear tooling has played a key role, and the inherent design flexibility, feature detail and surface quality offered by SL has led this technology into the mainstream. Footwear manufacturers continue to push for faster design iteration, shorter route to market and more cost- and time-efficient approaches.

DSM collaborated with key footwear manufacturers to develop an additive manufacturing material that addresses the specific needs for footwear tooling. Somos<sup>®</sup> Momentum offers high part accuracy, quality and fine feature detail. The outstanding accuracy of the resin allows the forming of sharp features which in turn enables the creation of detailed soles not only in initial design, but also translated into the aluminum mold. In addition, the pink color of the material makes it easy to discern key features in the design and to inspect the parts for surface defects. Taking this technology a step further, direct printing of the sole will omit the need for detailing or texturing, speeding up the traditional tooling process up to 60%, enabling a cost reduction up to 30%.

## Key Benefits

- Highest efficiency stereolithography material
- High accuracy and surface quality
- Complex shapes and feature detail
- Eliminates chemical texturing process
- Color facilitates inspection of feature detail and quality
- Overall cost saving during development and manufacturing



## Technical Data

| Liquid Properties |                                | Optical Properties |                         |  |
|-------------------|--------------------------------|--------------------|-------------------------|--|
| Appearance        | Opaque White                   | EC                 | 13.0 mJ/cm <sup>2</sup> | [critical exposure]                                  |
| Viscosity         | ~340 cps @ 30°C                | DP                 | 6.25 mils               | [slope of cure-depth vs. ln (E) curve]               |
| Density           | ~1.16 g/cm <sup>3</sup> @ 25°C | E10                | 64 mJ/cm <sup>2</sup>   | [exposure that gives 0.254 mm (.010 inch) thickness] |

| Mechanical Properties |                       | UV Postcure |               |
|-----------------------|-----------------------|-------------|---------------|
| ASTM Method           | Property Description  | Metric      | Imperial      |
| D638M                 | Tensile Modulus       | 2,510 MPa   | 364 ksi       |
| D638M                 | Tensile Strength      | 37 MPa      | 5.4 ksi       |
| D638M                 | Elongation at Break   | 7.5%        |               |
| D638M                 | Elongation at Yield   | 3%          |               |
| D790M                 | Flexural Strength     | 67.3 MPa    | 9.8 ksi       |
| D2240                 | Flexural Modulus      | 2,200 MPa   | 319 ksi       |
| D256A                 | Izod Impact (Notched) | 26 J/m      | 0.49 ft-lb/in |
| D638M                 | Poisson's Ratio       | 0.41        |               |
| D2240                 | Hardness (Shore D)    | 79          |               |
| D570-98               | Water Absorption      | 0.40%       |               |

| Thermal/Electrical Properties |                                  | UV Postcure |             |
|-------------------------------|----------------------------------|-------------|-------------|
| ASTM Method                   | Property Description             | Metric      | Imperial    |
| E831-05                       | C.T.E. -40 - 0°C (-40 - 32°F)    | 63 µm/m°C   | 35 µin/in°F |
| E831-05                       | C.T.E. 0 - 50°C (32 - 122°F)     | 89 µm/m°C   | 49 µin/in°F |
| E831-05                       | C.T.E. 50 - 100°C (122 - 212°F)  | 170 µm/m°C  | 95 µin/in°F |
| E831-05                       | C.T.E. 100 - 150°C (212 - 302°F) | 172 µm/m°C  | 96 µin/in°F |
| D150-98                       | Dielectric Constant 60 Hz        | 3.8         |             |
| D150-98                       | Dielectric Constant 1 KHz        | 3.7         |             |
| D150-98                       | Dielectric Constant 1 MHz        | 3.4         |             |
| D149-97A                      | Dielectric Strength              | 17.9 kV/mm  | 454 V/mil   |
| D648                          | HDT @ 0.46 MPa (66 psi)          | 46°C        | 115°F       |
| D648                          | HDT @ 1.81 MPa (264 psi)         | 41°C        | 106°F       |

*These values may vary and depend on individual machine processing and post-curing practices.*

### More information

For more information and buying options, please visit [www.dsm.com/additive-manufacturing/](http://www.dsm.com/additive-manufacturing/)

DSM – Bright Science. Brighter Living.™

All information supplied by or on behalf of DSM in relation to its products, whether in the nature of data, recommendations or otherwise, is supported by research and, in good faith, believed reliable, but DSM assumes no liability and makes no warranties of any kind, express or implied, including, but not limited to, those of title, merchantability, fitness for a particular purpose or non-infringement or any warranty arising from a course of dealing, usage, or trade practice whatsoever in respect of application, processing or use made of aforementioned information, or product. The user assumes all responsibility for the use of all information provided and shall verify quality and other properties or any consequences from the use of all such information. Somos® is a trademark of DSM.

Copyright © DSM 2019. All rights reserved. No part of the information may be reproduced, distributed, or transmitted in any form or by any means, including photocopying, recording, or other electronic or mechanical methods, without the prior written permission of DSM. Doc 0023-01